



Product Data Sheet

StretchFLEX III - - - 17.8 micron / .70 mil / 70 gauge - Stretch Film

Characteristics	Test	Values
Thickness		70 gauge / 0.70 mil / 17.8 micron
Width (inches)		20"
Length (feet)		6,000'
Net Weight / Roll (lbs. - nominal)		20" = 33.6 lbs.
Roll Diameter (O.D., inches)		9.05" (nominal)
Manufacturing Process		Mono-layer Blown
Ultimate Tensile MD (psi)	ASTM D 882	6800 psi
Ultimate Tensile TD (psi)	ASTM D 882	5600 psi
Elongation MD (%)	ASTM D 882	670%
Elongation TD (%)	ASTM D 882	825%
Prestretch	IPG / Lantech	450% (Breaking point)

Notice to Purchaser: All statements, technical information and recommendations herein are based on tests performed on clear Stretch Film products only and we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties, expressed or implied, including the implied warranties of merchantability and fitness for purpose. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, the user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.
NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE DIRECT, INCIDENTAL, OR CONSEQUENTIAL, ARISING OUT OF THE USE OR THE INABILITY TO USE THE PRODUCT.
No statement or recommendations not contained herein shall have any force or effect unless in an agreement signed by officers of seller and

“STRETCHING THE POSSIBILITIES”

Intertape Polymer Group - Sarasota, FL - Customer Service Telephone 800-567-8273