

527

MEDIUM TEMP MEDIUM GRADE PAPER MASKING TAPE

INTERTAPE POLYMER GROUP TECHNICAL DATA SHEET

DESCRIPTION

A beige, moisture-resistant crepe paper masking tape coated with a stain resistant pressure-sensitive natural rubber adhesive. Capable of withstanding bake temperatures up to 250°F (120°C) for one hour and/or exposure to ultra-violet (UV) light for up to five hours. Specially designed adhesive sticks firmly and securely to most surfaces with clean removal.

PRODUCT APPLICATION

Spray painting primarily aftermarket autos, boats, etc., wooden window manufacturing (temporary bonding), some PCB (printed circuit board) manufacturing, and any critical masking application requiring higher temperature resistance versus most general purpose masking tapes.

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard test. The data should not be considered as specifications.

Backing	Crepe Paper
Adhesive	Natural/Synthetic Rubber
Adhesion to Steel (oz/in of width) PSTC-1	33 (9 N/25mm)
Tensile Strength (lbs/in of width) PSTC-31	23 (100.7 N/25mm)
Elongation (at break) PSTC-31	7%
Total Thickness (mils) PSTC-33	6.1 (0.12mm)
Quick Stick to Steel (oz/in of width) PSTC-5	18 (4.9 N/25mm)
Color	Beige



3647 Cortez Road West | Bradenton, FL 34210 | USA
Customer Service: 800.IPG.8273 | 800.474.8273
Tape Technical Service: 877.447.4832
www.itape.com | info@itape.com



While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 02/11

