

ASJ1

'ALL SERVICE JACKET' SPECIALTY TAPE

DESCRIPTION

ASJ1 is an 'All Service Jacket' tape with an aggressive, long-lasting pressure-sensitive acrylic adhesive. All temperature rated, flame retardant, high shear adhesion, and UV resistant. Superior bonding when exposed to either sub-zero or elevated temperatures. Release coated kraft liner.

PRODUCT APPLICATIONS

Engineered for permanent joining, seaming and sealing of pipe insulation jackets, white FSK laminated blanket, duct board and flexible duct joints and seams to enhance appearance and maintain vapor barrier integrity. Also used for HVAC (Heating, Ventilation and Air Conditioning), pipe insulation wrap and butt-strip applications.

GOVERNMENT COMPLIANCE

UL-723 rated.



3647 Cortez Road West | Bradenton, FL 34210 | USA
Customer Service: 800.IPG.8273 | 800.474.8273
Tape Technical Service: 877.447.4832
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 02/11

INTERTAPE POLYMER GROUP TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard test. The data should not be considered as specifications.

Backing ASTM C-1136	ASJ (Type I ~ IV)
Adhesive	Acrylic
Tensile Strength MD ASTM D-3759	57 lb _f /in width (250 N/25mm)
Elongation (at break) ASTM D-3759	3%
Adhesion to Steel ASTM D-3330	> 100 oz/in (27.4 N/25 mm)
Total Thickness w/o liner ASTM D-3652	11.5 mil (0.29 mm)
Flame Spread UL-723 / ASTM E-84	10
Smoke Generated UL-723 / ASTM E-84	10
Operating Temperature Range	-35°F ~ +250°F (-37°C ~ +120°C)

